

- b) a non-blooming polymeric release agent/lubricant composed of olefinic monomeric units, wherein said release agent/lubricant is non-blooming when the metallized molded resin article is subject to aging at temperature of 150 -185 degrees Centigrade,
- c) optionally, from 0 to about 20 percent by weight nucleants and/or fillers,
- d) less than 5% by weight additional ingredients based on the total weight of the resin composition, and
- (e) a metallizing layer disposed on a portion of the surface of said article [being metallized].

Cancel claim 2.

Please amend claim 3 to read as follows:

3. (amended) A metallized molded resin article according to claim 1 wherein said mold release agent/lubricant is selected from the group consisting of polyethylene, poly-ethylene vinyl acetate (EVA), [or] poly-ethylene ethyl acrylate (EEA) [or] and mixtures thereof.

Cancel claim 5.

Please amend claim 8 to read as follows:

8. (amended) A metallized molded resin article according to claim 6 wherein the metallizing layer of the metallized article comprises aluminum.

Please amend claim 12 to read as follows:

12. (amended) A process for making a metallized molded resin article comprising the steps of

a) forming a resin mixture consisting essentially [from about] of
70 to about 99.9 weight percent, based on the total weight of the resin composition, of a crystallizable polyester resin derived from aliphatic or cycloaliphatic diols, or mixtures thereof, containing 2 to 10 carbon atoms and at least one aromatic dicarboxylic acid wherein the aromatic group is a C6 to C20 aryl radical,